

TECHNICAL DATA SHEET

BK CB-520

OXIDIZING / ANTIQUE FINISH ON COPPER AND BRASS

BK CB-520 is formulated liquid concentrate to produce antique finish by immersion process on copper and brass articles. Wide range of colours can be obtained by varying concentration and time.

MAKE UP :

FOR BLACK COLOUR

BK CB-520	250 ml
Water	750 ml
Temperature	Room
Time	40-180 seconds

EQUIPMENT:

PP, PVC or rubber tanks and filter are recommended.

CONTROL:

The colouring process is a chemical reaction between solution and metal surface. When the immersion time required to produce desired colour increases add BK CB-520 to reduce immersion time to previous duration.

CAUTION:

Avoid the contact with skin and eyes. Wear protective clothing and face shield. In case of contact with skin and eyes wash with plenty of water and obtain medical attention.

DISCLAIMER:

The data forth in this Bulletin is delivered by **SHARMA CHEMINDUS PVT LTD.** to be true, accurate and complete but is not guaranteed. Our sole warranty is as stated in our standard Terms and Conditions of sale. We cannot warrant that our customers will achieve the same results from any bulletin because we do not have control either over the condition of use; nor we assume any of our products in a manner which infringes the patents of third parties.