

## TECHNICAL DATA SHEET

### METFIX ZN CONDITIONER

Metfix Zn conditioner is a titanium based conditioning agent for iron and steel prior to zinc phosphating to obtain dense and fine crystalline zinc phosphate coating. Properly cleaned article should be processed prior to Metfix Zn conditioner.

#### MAKE UP- ( 1000 Lts.)

Metfix Zn conditioner	1-2 Kgs
Temperature	20 - 40°C
Time	30-90 Seconds

This bath is controlled by pH and no analytical test is required.

The Bath loses its efficiency on prolonged use and needs to be prepared fresh.

#### DISCLAIMER:

The data forth in this Bulletin is delivered by **SHARMA CHEMINDUS PVT LTD.** to be true, accurate and complete but is not guaranteed. Our sole warranty is as stated in our standard Terms and Conditions of sale. We cannot warrant that our customers will achieve the same results from any bulletin because we do not have control either over the condition of use; nor we assume any of our products in a manner which infringes the parties.