

TECHNICAL DATA SHEET

CUMAX AC-582

PROCESS :

CUMAX AC 582 :

- Is an acid Copper plating process.
- Produces highest brightness and most brilliant deposits.
- Deposits are low stressed and ductile Copper.
- Is for functional and decorative applications.
- Shows high leveling coupled with good throwing power.
- Gives high corrosion resistance and is suited for steel , zinc , die cast and plating on plastics.

PRODUCTS :

CUMAX AC 582: Make up solution and for maintenance along
With CUMAX AC 583 for uniform **bright**
deposits.

CUMAX AC 583 : Make up solution and for maintenance along
With CUMAX AC 582 for **leveling** over the
entire current density.

CUMAX AC 584 : To be used for extra ductility.

PLATING:

Tank material : Steel lined with rubber , PP or PVC coating.

Anodes : Phosphorous Copper , 99.9% (0.02 – 0.06 %
phosphorous content)

Cooling / Heating : Cooling and heating can be needed to keep

the electrolyte in a certain temperature range.

(20 – 35°C).

Filtration :

Continuously at 1 - 5 bath volumes / hour.

Agitation :

Air agitation (oil and dust free compressed air)

in additional mechanical agitation is

recommended

Voltage :

1.5 – 6.0 V

Cathodic current density :

Barrel -0.5 – 1.0 A / dm²

Rack - 1.0 – 6.0 A / dm²

Anodic current density :

0.5 – 2.5 A / dm²

Temperature :

20 – 35°C

pH :

< 1

Concentration :

	Optimum	Range
COPPER metal	55 g/l	50 – 60 g/l
Copper sulphate	220 g/l	190 – 240 g/l
Sulphuric acid	65 g/l	60 – 70 g/l
Chloride content	100 mg/l	90 – 120 mg/l
CUMAX AC 582	10 ml/l	8 - 12 ml/l
CUMAX AC 583	0.7 ml/l	0.5 – 0.9 ml/l
CUMAX AC 584	0.1 ml/l	optional

Make up procedure :

- Fill a separate tank with 50 % DM water.
- Add required quantity of Copper sulphate (5 H₂O).
- Add activated carbon 2 g / l and stir for 1 hour till the solution becomes clear.
- Now add sulphuric acid and chloride into the solution.
- Make up with DM water upto 90 % of the final volume and cool down to room temperature.
- Fill upto the final volume with DM water.
- Then add **CUMAX AC 582, CUMAX AC 583 and CUMAX AC 584** and stir well.
- Add (25 – 28 ml) HCL for 100 lts bath.
- Check chloride concentration and make sure Chloride mg / l (ppm) does not exceed 120 ppm.

Copper content :

The Copper concentration should be kept in the required analytical ranges. If the concentration decreases drastically, it can cause burns in high current density areas or poor leveling in the low current density areas.

Chloride Content :

The chloride content must be kept in recommended range. An excess of chloride reduces the leveling and a lack of chloride reduces the degree of brightness. If the addition **CUMAX AC 582** additives does not show any effect, please check the chloride content.

For increase of 1 mg (ppm) of chloride in 1000 lts bath add 1.65 gms of sodium chloride.

Sulphuric Acid :

The sulphuric acid content should be in recommended ranges and always lower than 80 g / l., for increase of 1 g / l of sulphuric acid (density 1.84) in 1000 ltr bath add 1 kg sulphuric acid.

Consumption for 1000 amp H :

CUMAX AC 582 100-200 ml

CUMAX AC 583 50-100 ml

CUMAX AC 584

Only for extra ductility.

Above consumption figures are given as rough guide lines for both maintenance. These may vary depending upon the degree of brightness and leveling required.

Both brightener **CUMAX AC 582 and CUMAX AC 583** have to be replenished at regular intervals.

To remove the organic contaminations active carbon treatment is recommended.

DISCLAIMER:

The data forth in this Bulletin is delivered by **SHARMA CHEMINDUS PVT LTD.** to be true, accurate and complete but is not guaranteed. Our sole warranty is as stated in our standard Terms and Conditions of sale. We cannot warrant that our customers will achieve the same results from any bulletin because we do not have control either over the condition of use; nor we assume any of our products in a manner which infringes the patents of third parties.