

TECHNICAL DATA SHEET

ANTIPIT 10

Antipit 10 is a liquid product used to remove surface tension in the solultion so that the hydrogen gas does not adhere to the surface thereby eliminating pitting in nickel plating solutions.

MAINTENANCE:

The Antipit 10 is to be added only when the pitting tendency is observed on the plated parts or when the foaming is too low in the nickel bath. Moreover, all the brightening agents do contain required amount of antipiting agents and hence regular additions are normally not required.

However when the solution is given batch carbon treatment, the Antipiting agents gets consumed and so we recommend an addition of 0.2-0.3 cc/l of Antipit 10.

DISCLAIMER:

The data forth in this Bulletin is delivered by **SHARMA CHEMINDUS PVT LTD.** to be true, accurate and complete but is not guaranteed. Our sole warranty is as stated in our standard Terms and Conditions of sale. We cannot warrant that our customers will achieve the same results from any bulletin because we do not have control either over the condition of use; nor we assume any of our products in a manner which infringes the parties.